

NO-1198-128

THE INFLUENCE OF PARTICLE PROPERTIES ON THE ROOM
TEMPERATURE COMPACTION 0 (U) NAVAL AIR DEVELOPMENT
CENTER WARMINSTER PA AIR VEHICLE AND CR


171


UNCLASSIFIED

J J REILLY ET AL APR 88 NADC-88026-60

F/G 11/9

NL





4

REPORT NO. NADC-88026-60

DTIC FILE 1000



THE INFLUENCE OF PARTICLE PROPERTIES ON THE ROOM TEMPERATURE COMPACTION OF POLYETHER-ETHERKETONE (PEEK) POWDERS

AD-A198 126

J. J. Reilly
NAVAL AIR DEVELOPMENT CENTER
Air Vehicle and Crew Systems Technology Department
Warminster, PA 18974-5000

and

I. L. Kamel
DREXEL UNIVERSITY
Department of Materials Engineering
Philadelphia, PA 19104

APRIL 1988

FINAL REPORT
Work Unit ZM570

DTIC
ELECTE
AUG 16 1988
S D
H

Approved for Public Release, Distribution Unlimited

Prepared for
NAVY EXPLORATORY DEVELOPMENT PROGRAM
AIRBORNE MATERIALS
(NA2A)

82 8 17 1988

NOTICES

REPORT NUMBERING SYSTEM - The numbering of technical project reports issued by the Naval Air Development Center is arranged for specific identification purposes. Each number consists of the Center acronym, the calendar year in which the number was assigned, the sequence number of the report within the specific calendar year, and the official 2-digit correspondence code of the Command Office or the Functional Department responsible for the report. For example: Report No. NADC-86015-70 indicates the fifteenth Center report for the year 1986 and prepared by the Systems and Software Technology Department. The numerical codes are as follows:

CODE	OFFICE OR DEPARTMENT
00	Commander, Naval Air Development Center
01	Technical Director, Naval Air Development Center
02	Comptroller
05	Computer Department
07	Planning Assessment Resources Department
10	Anti-Submarine Warfare Systems Department
20	Tactical Air Systems Department
30	Battle Force Systems Department
40	Communication & Navigation Technology Department
50	Mission Avionics Technology Department
60	Air Vehicle & Crew Systems Technology Department
70	Systems & Software Technology Department
80	Engineering Support Group

PRODUCT ENDORSEMENT - The discussion or instructions concerning commercial products herein do not constitute an endorsement by the Government nor do they convey or imply the license or right to use such products.

APPROVED BY:

Donald P. McErlean

DATE:

4/25/88

DONALD P. McERLEAN
HEAD, AIR VEHICLE & CREW SYSTEMS
TECHNOLOGY DEPARTMENT

REPORT DOCUMENTATION PAGE

1a REPORT SECURITY CLASSIFICATION UNCLASSIFIED			1b RESTRICTIVE MARKINGS N/A		
2a SECURITY CLASSIFICATION AUTHORITY			3 DISTRIBUTION/AVAILABILITY OF REPORT Approved for Public Release; Distribution Unlimited		
2b DECLASSIFICATION/DOWNGRADING SCHEDULE					
4 PERFORMING ORGANIZATION REPORT NUMBER(S) NADC-88026-60			5. MONITORING ORGANIZATION REPORT NUMBER(S) N/A		
6a NAME OF PERFORMING ORGANIZATION Naval Air Development Center		6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION N/A		
6c ADDRESS (City, State, and ZIP Code) Warminster, PA 18974-5000			7b. ADDRESS (City, State, and ZIP Code) N/A		
8a. NAME OF FUNDING / SPONSORING ORGANIZATION NADC		8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N/A		
8c ADDRESS (City, State, and ZIP Code) Warminster, PA 18974-5000			10. SOURCE OF FUNDING NUMBERS		
			PROGRAM ELEMENT NO. 62234N	PROJECT NO. RS34A52	TASK NO. 4
					WORK UNIT ACCESSION NO. 681081
11 TITLE (Include Security Classification) The Influence of Particle Properties on the Room Temperature Compaction of Polyether-Etherketone (PEEK) Powders					
12 PERSONAL AUTHOR(S) J. J. Reilly and I. L. Kamel					
13a TYPE OF REPORT		13b. TIME COVERED FROM AUG 86 TO AUG 87		14. DATE OF REPORT (Year, Month, Day) 1988 APRIL	
				15 PAGE COUNT 41	
16 SUPPLEMENTARY NOTATION					
17 COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP	Compaction, Thermal Analysis, PEEK, Powders, Viscoelectric Recovery, Green Properties		
11	09				
19 ABSTRACT (Continue on reverse if necessary and identify by block number) <p>→ This study deals with the characterization and cold compaction of polyether-etherketone (PEEK) powders. Four different types of PEEK powders, which are commercially available from Imperial Chemical Industries (ICI) were characterized for density, crystallinity, particle size, particle size distribution and particle morphology. Fine and coarse size powders of a low viscosity grade (150PF and 150P) and similar powders of a high viscosity grade (450PF and 450P) were processed. Compaction was successful at room temperature using the 150 grade powders but not with the 450 grade powders. Compressibility curves were obtained at room temperature for the 150 grade powders and their post-compaction viscoelastic recoveries were measured. Both coarse and fine size powders of the 150 grade reached relative plateau densities of 95.8% and 95.1% when compacted at pressures exceeding 300 MPa. These high densification values at room temperature were associated with minimal post-compaction viscoelastic recoveries and as-compacted strengths as high as 8.9 MPa. A modified densification parameter (DP*) was developed based on the plastic deformation of the crystalline regions alone. This new dimensionless parameter, DP*, demonstrated a better fit of all the compaction data. The transverse rupture strength and the green density data are presented and explained in terms of this DP*. (AWJ)</p>					
20 DISTRIBUTION/AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION UNCLASSIFIED		
22a NAME OF RESPONSIBLE INDIVIDUAL John .I Reilly			22b TELEPHONE (Include Area Code) 215-441-1924		22c OFFICE SYMBOL

TABLE OF CONTENTS

	Page
LIST OF TABLES	ii
LIST OF FIGURES	iii
INTRODUCTION	1
EXPERIMENTAL PROCEDURE	2
POWDER CHARACTERIZATION	2
COMPACTION	3
RESULTS	3
POWDER CHARACTERIZATION	3
COMPACTION	11
A DENSIFICATION PARAMETER FOR PEEK POWDERS COMPACTED AT ROOM TEMPERATURE.....	14
DISCUSSION	25
CONCLUSIONS	29
RECOMMENDATIONS FOR FUTURE WORK	30
ACKNOWLEDGEMENTS	30
LIST OF REFERENCES	31



Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

LIST OF TABLES

Table	Page
1. PEEK Powder Density Results.....	4
2. DSC Results.....	4
3. PEEK Powder Characteristics.....	11

LIST OF FIGURES

Figure	Page
1. DSC Thermogram of 450PF Powder.....	5
2. SEM Photomicrographs of 150P Powder.....	7
3. SEM Photomicrographs of 150PF Powder.....	8
4. SEM Photomicrographs of 450PF Powder.....	9
5. SEM Photomicrographs of Annealed 450PF Powder.....	10
6. Particle Size Distributions for Commercial PEEK Powders.....	12
7. Relative Green Density of 150 Grade PEEK versus Compaction Pressure.....	13
8. Transverse Rupture Strength versus Relative Green Density for 150 Grade PEEK.....	15
9. SEM Photomicrographs of 150PF Fracture Surface.....	16
10. SEM Photomicrographs of 150P Fracture Surface.....	17
11. Viscoelastic Recovery as a Function of Relaxation Time for 150 Grade PEEK.....	18
12. Densification Parameter versus Compaction Pressure for 150 Grade PEEK Samples.....	20
13. Transverse Rupture Strength versus Densification Parameter for 150 Grade Compacts.....	21
14. The Compaction Process (a) Apparent Volume (V_a) Before Compaction in the Die, (b) Approximate Theoretical Powder Volume (V_t) When Under Pressure in the Plateau Region (P_{pr}) and (c) the Green Volume of the Compact 24 hrs. After Ejection From the Die.....	22
15. Modified Densification Parameter versus Compaction Pressure for 150 Grade PEEK Samples.....	26
16. Transverse Rupture Strength versus Modified Densification Parameter for 150 Grade PEEK Samples.....	27

INTRODUCTION

High temperature thermoplastics like polytetra-fluoroethylene (PTFE), Upjohn polyimide 2080 (PI), poly-phenylene sulfide (PPS) and polyether-etherketone (PEEK) are relatively difficult to process by the conventional melt processing techniques, for several reasons. PTFE is a semicrystalline thermoplastic with a glass transition temperature (T_g) of 126°C and a melting temperature (T_m) of 342°C [1]. The application of powder metallurgy (P/M) techniques to polymers started with the processing of PTFE because of its high melt viscosity and its high T_m [2]. PI-2080 is an amorphous polymer with a T_g in the range of 310 - 315°C [3,4]. Due to its high melt viscosity, compression molding is the primary technique used to form this polymer [3]. In addition, it is necessary to thermally cycle the mold to achieve quality components [4]. This latter molding requirement adversely affects the economics of using this technique in production because of its time and energy inefficiencies [4]. PPS and PEEK are also semicrystalline thermoplastics with T_g 's of 85°C and 144°C , and T_m 's of 285°C and 335°C , respectively [5-9]. Because both of these polymers have high melting temperatures, melt processing techniques require the use of high temperature molding equipment which results in high capital and energy costs. In particular, PEEK possesses a combination of high viscosity and low crystallization rates which make melt processing economically unattractive. Processing PEEK via conventional techniques such as injection molding and extrusion have been previously described [10-12]. An alternative processing technique is direct powder compaction and preform sintering. This approach eliminates the pelletizing step, reduces the need for recrystallization via annealing and is accommodating to the inclusion of hard fillers. However, this P/M approach suffers from a lengthy sintering step if conventional oven heating of the preform is utilized. Thermoplastics are good heat insulators and therefore, sintering times exceeding 30 minutes may be expected for parts in the one inch thickness range. Several possible alternatives [13] may be used to overcome this slow process including the use of induction heating of magnetic fillers [14-16], radio frequency or microwave heating of fillers with high dielectric loss properties [17,18] or particle fusion by ultrasonic compaction [18]. These approaches efficiently supply energy to the polymer particle surfaces where it is needed for consolidation and eliminates the need for melting and shearing the entire polymer mass. This is particularly significant for those polymers with narrow processing temperature ranges or ones which are sensitive to shear deformations during melt flow. The conservation of energy and the reduction of cycle time with these techniques make them very attractive for the processing of PEEK and other high performance thermoplastics. Additionally, a forging process may be used following sintering if necessary, to reshape and consolidate the sintered compacts while realizing the benefits of predesigned orientations.

Most studies [3,4,18-37] on polymer powder compaction have been performed using glassy polymers, thermosets, semicrystalline thermoplastics and polymer blends. The results of these investigations indicate that powder particle size, particle morphology, compaction rate, compaction pressure and dwell time at peak pressure are parameters which

significantly influence the compaction process. This report deals with the compaction properties of a semicrystalline thermoplastic (PEEK) at temperatures significantly below its T_g. Compaction rate and dwell time at peak pressure are held constant in this study while the influences of crystallinity, particle size and particle surface properties on compaction efficiency are discussed.

The specific objectives of this report are to physically and morphologically characterize four different commercial PEEK powders and to explain their behavior when compacted at room temperature. Very little work has dealt with the compaction of semicrystalline polymers below their T_g. Bigg [30,31] tried to compact nylon 11 below its T_g. However, the compacted particles relaxed so much during sintering that they could not be handled or tested for strength. This type of behavior occurred because the nylon 11 particles were not plastically deformed sufficiently during compaction to form permanent interlocking junctions which provide green strength. Radhakrishnan and Nadkarni [36] compacted PPS below its T_g to study compaction-induced changes in crystallinity. However, they did not report green density or green strength values. The work involved in this report will show the advantages of cold compaction of a semi-crystalline polymer at temperatures significantly below its T_g. Currently, the authors are also extending this study of PEEK powder compaction to include mixtures of PEEK and nickel powders [38].

EXPERIMENTAL PROCEDURE

POWDER CHARACTERIZATION

Commercially available high viscosity (450PF, 450P) and low viscosity (150PF, 150P) grades of PEEK powders were obtained from Imperial Chemical Industries (ICI). Particle size and particle size distribution properties were determined using sieve analysis in accordance with ASTM Standard D1921-63 (reapproved 1975), Method A. Apparent densities were measured in accordance with ASTM Standard D1895-69 (reapproved 1979), Method A. The powder densities were measured with a Micromeritics (Norcross, GA) AutoPycnometer 1320 using helium. Weight percent crystallinity values were calculated from these density measurements using 1.401 g/cc and 1.263 g/cc as the respective 100% crystalline and amorphous densities [9]. Tap density tests were performed by transferring a weighed sample of powder into a graduated cylinder, tapping the cylinder from a height of one inch onto a padded surface until the volume became constant (usually about 100 times), and then measuring the volume. Scanning electron microscopy (SEM) was used to characterize particle surfaces. The SEM samples were prepared by dispersing the powder onto adhesive tape, sputtering the surface with a thin layer of gold and then examining under the SEM (AMR Model 1000A) at 20 kV.

Crystallinities of the as-received, annealed and melt recrystallized powders were measured using a DuPont 910 differential scanning calorimeter (DSC) controlled by a 1090 thermal analyzer. Each specimen was heated at

a rate of 5°C/min. up to 500°C, then cooled to 100°C at a rate of 10°C/min., held at 100°C for 10 min. and then reheated to 500°C at a rate of 5°C/min. The temperatures and latent heats of crystallization and fusion were determined from the areas under the various peaks of the thermogram. This data was converted to weight percent crystallinity values using 130 J/g as the heat of fusion for 100% crystalline PEEK [18].

COMPACTION

The powders were compacted in a Tinius Olsen press using a Haller double-acting die with a one minute dwell time at peak pressure and without the use of a lubricant. The velocity of the punch at zero pressure was approximately 5 cm/min. Cylindrical (2.54 cm diameter) and rectangular (1.27 cm by 3.18 cm) dies were used to fabricate specimens. Green density was determined by measuring the weight and dimensions (24 hrs after compaction) of the samples. These values were used to evaluate compressibility as a function of compaction pressure. Viscoelastic recovery of the cylindrical powder compacts at room temperature was determined as a function of time after ejection. For this purpose, low melt viscosity PEEK specimens were compacted at room temperature using 400 MPa of pressure. Transverse rupture strengths of rectangular compacts (0.635 cm thick) were determined in accordance with ASTM Standard B312-82 at a crosshead speed of 0.5 cm/min. These green strength values were evaluated as a function of density. The SEM was also used to examine the fracture surfaces of these specimens.

RESULTS

POWDER CHARACTERIZATION

Powder density results determined using a gas pycnometer are listed in Table 1. Densities ranged from 1.281 g/cc to 1.318 g/cc for the as-received PEEK powders. Weight percent crystallinity values calculated from these density measurements are also included in Table 1. Both fine-sized powders (PF designated) had much lower densities and consequently significantly lower degrees of crystallinity than the coarse-sized powders. These values ranged from 14 to 42 percent crystallinity for the as-received powders. The last powder listed in Table 1 (annealed 450PF) was exposed to a temperature of 210°C for 2 hours and then oven-cooled to room temperature before testing. This annealed powder showed an increase of 15% in crystallinity compared to its as-received condition.

DSC was also used to determine weight percent crystallinity values by measuring the enthalpy of fusion. These results are shown in Table 2. This technique confirms that the 450PF material is not fully crystallized in the as-received condition and therefore, will continue to do so when its temperature is raised above its T_g as shown in Fig. 1. This plot is a typical thermogram from a DSC run on a sample of 450PF powder. A pre-melt

TABLE 1: POWDER DENSITY RESULTS

MATERIAL	DENSITY (g/cc)	PERCENT CRYSTAL- LINITY
150PF	1.301	30
150P	1.318	42
450PF	1.281	14
450P	1.313	39
*450PF	1.300	29

* Annealed at 210°C for 2 hours.

TABLE 2: DSC RESULTS

MATERIAL	CONDITION	HEAT OF TRANSITION (J/g)	PEAK TRANSITION TEMPERATURE (°C)	PERCENT CRYSTAL- LINITY
150PF	AS-RECEIVED	50	342	38
	RECRYSTALLIZED FROM MELT	32	249	25
	RE-MELTED	28	326	21
150P	AS-RECEIVED	56	343	43
	RECRYSTALLIZED FROM MELT	56	297	43
	RE-MELTED	37	338	28
450PF	PRE-MELT CRYSTALLIZATION	16	168	12
	AS-RECEIVED (ANNEALED)	44	338	34
	AS-RECEIVED (CALCULATED)	29		22
	RECRYSTALLIZED FROM MELT	41	255	32
	RE-MELTED	38	332	29
450P	AS-RECEIVED	52	334	40
	RECRYSTALLIZED FROM MELT	25	268	19
	RE-MELTED	28	331	22




Figure 1 - DSC Thermogram of 450PF Powder

crystallization peak which occurs at about 168°C is apparent in Fig. 1. The heat of pre-melt crystallization at 168°C was subtracted from the heat of fusion peak at the normal melting point and the difference is listed as the as-received (calculated) crystallinity for the 450PF powder.

The peak crystalline melting point of the powders ranged from 334°C to 342°C. The percent crystallinity values determined for the as-received coarse powders (150P and 450P) using density data were within one percent of their respective values as determined by the heat of fusion technique. However, a similar comparison of the two techniques for the fine particles (150PF and 450PF) revealed differences of about 8 percent. Several reasons may be put forth to explain these differences. The DSC technique is most effectively used to determine the percent crystallinity of highly ordered materials with sharp, well-defined melting peaks [39]. The PEEK powders studied in this investigation (especially the fine-sized powders) did not have the above characteristics so the baseline was extrapolated across these broad peaks, which may have introduced additional error. However, the relative values of crystallinity are consistent within each of the above techniques.

After heating the powders through the melting point and recrystallizing, the crystallinities determined from a second melting peak decreased by 5 to 18 percent compared to those obtained during the first melt of each powder. The peak melting points decreased by 3-16°C upon remelting which also indicates a reduction in order when PEEK is cooled from the melt at a rate of 10°C/min. The heats of recrystallization and second melting peaks have fairly close values but some differences are to be expected due to the temperature dependence of the 100% crystalline heat of fusion value used in these calculations. In some instances, the recrystallization process produced a complex peak which appeared to be a combination of two peaks. This observation is in accord with the dual crystallization mechanism for PEEK proposed by Velisaris and Seferis [40].

SEM photographs of the PEEK particles are shown in Figs. 2-5. Fig. 2 is a photograph of the 150P powder which is very similar in appearance to the 450P powder. Both of these powders appear to be almost equiaxed with relatively smooth surfaces. Figs. 3 and 4 show the 150PF and 450PF powders, respectively to be much smaller in size compared to the coarse-sized powders. These fine-sized powders are also seen to be irregularly shaped with fairly rough surfaces. This is particularly evident in Fig. 4 for the 450PF powder where it appears as though some of the particles have been deformed to the extent of fiber formation. Figs. 4 and 5 reveal that the as-received and the annealed 450PF powders are similar. This is indicative of plastic deformation in the as-received 450PF powder which will not be significantly affected by annealing.

Several powder characteristics are summarized in Table 3. The apparent or bulk density provides a measure of the volume the powder will occupy at zero pressure. The primary importance of this parameter is realized when storage volume or tooling size needs to be determined. Apparent densities ranged from 0.37 to 0.49 g/cc. The 150PF and 150P powders have compression ratios (green density/apparent density) of 3.0 and 3.3, respectively at their maximum green densification levels.



100U




100U

Figure 2 - SEM Photomicrographs of 150P Powder



1000



1000

Figure 3 - SEM Photomicrographs of 150PF Powder





Figure 4 - SEM Photomicrographs of 450PF Powder



Figure 5 - SEM Photomicrographs of Annealed 450 PF Powder

TABLE 3: POWDER CHARACTERISTICS

MATERIAL	APPARENT DENSITY (g/cc)	TAP DENSITY (g/cc)	MEAN PARTICLE DIAMETER (μ m)
150PF	0.42	0.57	145
150P	0.38	0.45	530
450PF	0.37	0.52	170
450P	0.49	0.53	680

The tap densities varied from 0.45 to 0.57 g/cc. The percent increase in apparent density due to tapping is attributable to interparticle arrangements. These percent increase values for the 150PF, 150P, 450PF and 450P powders (calculated from Table 3) are 36, 18, 41 and 8, respectively. Note that the fine-sized powders of each grade have higher percent increases in apparent density after tapping. This is in part due to the rough irregular surfaces of the 150PF and 450PF powders (Figs. 3 and 4). These rough surfaces cause high interparticle friction levels compared to the smoother surfaces of the coarse-sized particles (Fig. 2). The tapping action provides enough energy to overcome the barriers to interparticle motion and allows the fine-sized powders to pack efficiently.

The mean particle diameter for each of these powders is also shown in Table 3. These values ranged from 145 μ m to 680 μ m. The fine and coarse 450 grade powders are slightly larger than the similar 150 grade powders. The coarse-sized powders of each grade are approximately four times the size of their respective fine-sized powders. The particle size distributions for these powders are shown in Fig. 6. The coarse-sized particles of each grade have broader distributions than the fine-sized particles. Each coarse-sized powder has a significant weight fraction of particles greater than the largest sieve size used.

COMPACTION

Compaction of each of the four different PEEK powders was attempted at room temperature. The 150 grade powders were pressed into quality compacts of good integrity that were easy to handle while both 450 grade powders crumbled when attempting to remove them from the die. Relative green density (green density/theoretical powder density) versus compaction pressure is plotted in Fig. 7 for 150P and 150PF powders. These powders densified with increasing compaction pressure until a constant densification level was reached. The plateau densification level for these compacts is reached at about 300 MPa (plateau pressure). The relative plateau densities (plateau density/theoretical powder density) of the 150PF and 150P powders were 95.8% and 95.1%, respectively. It is seen




Figure 6 - Particle Size Distributions for Commercial PEEK Powders




Figure 7 - Relative Green Density of 150 Grade PEEK versus Compaction Pressure

from Fig. 7 that the fine-sized powder (150PF) achieved a higher relative plateau density than the coarse-sized powder (150P), respectively. This observation will be discussed in the next section.

A graph of transverse rupture strength as a function of relative green density is shown in Fig. 8. Both 150 grade compacts displayed comparable strength versus density with the 150P material being slightly stronger. Strength values as high as 8.9 MPa and 7.6 MPa were measured for the 150P and 150PF samples, respectively. Compacts which had a relative green density less than 55 percent crumbled quite readily even with delicate handling. The fracture surfaces of 150PF and 150P specimens which were compacted at a pressure of 614 MPa are shown in Figs. 9 and 10, respectively. The individual particle boundaries are visible in both these figures and the mode of fracture appears to be along these boundaries. Figs. 9 and 10 both show a large amount of plastic deformation. A comparison of these figures reveals that the 150P material experienced a greater degree of plastic deformation which resulted in better mechanical interlocking of particles and therefore, higher strengths.

Room temperature viscoelastic recovery data for the 150 grade specimens in the axial and radial directions expressed as a function of time after compaction at 400 MPa are shown in Fig. 11. The dimensional changes in the 150P compacts are slightly greater than that of the 150PF compacts. However, on a volume change basis, they exhibit almost identical behavior (0.16% versus 0.15%). The 150PF and 150P compacts displayed equilibrium axial expansions of about 0.24% and 0.36% relative to their thicknesses 24 hours after compaction, and radial contractions of 0.28% and 0.31% relative to the die diameter, respectively. The elastic portion of the recovery in the radial direction for the 150PF and 150P specimens was -0.06% and -0.09%, respectively. The dimensions in the radial and axial directions are almost completely stable within 24 hours after ejection from the die.

A DENSIFICATION PARAMETER FOR PEEK POWDERS COMPACTED AT ROOM TEMPERATURE

It was observed from Fig. 7 that the 150PF (fine-sized) compacts achieved higher relative plateau densities than the 150P (coarse-sized) compacts. However, it was observed from Fig. 8 that the 150PF compacts were not as strong as the 150P compacts. The combination of the above observations was unexpected for a couple of different reasons. First, previous work [19,26,28,35] has indicated that the higher the relative plateau density of a particular polymer, the stronger the resultant compact. This seems logical if it is assumed that a uniform void size distribution is achieved in the resultant compact. Secondly, it has been reported [3,18-20,26] that the smaller the average particle size of a specific polymer, the higher the resultant green strength. This trend was reasoned in one paper [19] based on the number of interparticle contact points. The present results with the 150 grade PEEK compacts contradict




Figure 8 - Transverse Rupture Strength versus Relative Green Density for 150 Grade PEEK




Figure 9 - SEM Photomicrographs of 150PF Fracture Surface




Figure 10 - SEM Photomicrographs of 150P Fracture Surface




Figure 11 - Viscoelastic Recovery as a Function of Relaxation Time for 150 Grade PEEK

both of the above statements which were gleaned from previous investigations.

These disagreements could be due to differences in the apparent densities. Therefore, compressibility curves have been normalized using a densification parameter (DP) [28,32] which eliminates the initial differences between powders due to variations in apparent density. The DP represents the fractional densification and is defined by:

$$DP = (Dg - Da)/(Dt - Da) \quad (1)$$

where, Dg - green density
Da - apparent density
Dt - theoretical powder density

A plot of the compressibility curves for the 150 grade materials using this DP is shown in Fig. 12. However, this is the same relative order of densification that was seen in Fig. 7. Similarly a graph of transverse rupture strength versus DP for these materials is shown in Fig. 13. Again it is seen that Fig. 13 is very similar to Fig. 8. Hence, the differences in the apparent densities are not the cause of the above disagreements.

Another possible reason for these contradictions is described as follows. Upon examination it can be seen that an assumption is made in using this DP to measure compaction efficiency. This assumption is that the entire polymer (both the crystalline and amorphous domains) plastically deform uniformly. This assumption may be valid for semicrystalline polymers compacted above Tg but not for ones compacted significantly below Tg as in the present case with PEEK. In order to modify this DP for semicrystalline polymers compacted below Tg, new assumptions need to be introduced.

Fig. 14 illustrates the current polymer powder compaction process. Initially the die is filled with powder which has a volume, Va, based on its apparent density (Fig. 14a). The apparent density is equal to the mass of the powder (M) divided by the apparent volume (Va). This apparent volume is comprised of the volume occupied by the powder (Vt) plus the volume of voids (Vv). The specimen is then compacted in a die using a pressure in the plateau region of the compressibility curve (Fig. 14b). While under this high pressure, the volume of porosity is approximately zero. Hence, the specimen under pressure has about the same density as the as-received powder, and occupies a volume, Vt. Upon ejection from the die, the green compact elastically recovers. The volume of the compact 24 hours after removal from the die (Fig. 14c) is named the green volume (Vg). This Vg is comprised of the powder volume (Vt) plus the volume of voids (Vv') introduced by the elastic and viscoelastic recovery processes.

The above description of the compaction process is valid for all classes of polymers. In the following discussion several assumptions are made based on applicable literature and on intuition in order to explain the behavior of PEEK powders compacted at room temperature. Previous findings [41] indicate that the deformation in most semicrystalline thermoplastics is initiated in the amorphous domains of the polymer. This




Figure 12 - Densification Parameter versus Compaction Pressure for 150 Grade PEEK Samples




Figure 13 - Transverse Rupture Strength versus Densification Parameter for 150 Grade Compacts




Figure 14 - The Compaction Process (a) Apparent Volume (V_a) Before Compaction in the Die, (b) Approximate Theoretical Powder Volume (V_t) When Under Pressure in the Plateau Region (P_{pr}) and (c) the Green Volume of the Compact 24 hrs. After Ejection From the Die

is because the amorphous domains are usually weaker than the highly ordered crystalline domains. This generalization also appears to be true for PEEK based on data reported by Kemmish and Hay [42]. Their data indicates that increases in the degree of crystallinity results in marked increases in the yield strength and slight increases in the yield strain. The first assumption is based on these statements. This assumption is that during compaction, the amorphous domains are initially deformed elastically but are restricted in deformation by the crystalline domains and by the limited chain mobility when the temperature is below T_g . Following this initial deformation, further elastic deformation occurs in both the amorphous and crystalline domains until the elastic limit is reached. Once this elastic limit is exceeded, plastic deformation occurs.

It is readily apparent from the microscopy and green density results that the PEEK powders do undergo plastic deformation during compaction. However, it is not clear as to where within the polymer (i.e. amorphous or crystalline domains) this deformation occurs. Karbach [43] has investigated the plastic deformation of thin films of melt-spun PEEK below their T_g . He found that by deforming the polymer perpendicular to the initial chain axes that a 90° rotation of the chain orientation occurred. He also reported that by deforming these PEEK films parallel to the initial axes that an extended lamellar morphology resulted.

It has also been reported [44,45] that entanglements in the amorphous domains of UHMWPE prevented it from fully crystallizing. This statement was deduced from the following. UHMWPE was exposed to low doses of radiation which caused chain scissions. These scissions were believed to have occurred on chains at the points of these high energy entanglements. Once the scissions occurred and these entanglements were removed, an increase in the degree of crystallinity was observed. This indicated that the segments at the interfaces between the crystalline and amorphous domains were under strain due to these entanglements and were prevented from crystallizing. The relatively low degrees of crystallinity for these PEEK powders compared to other semicrystalline polymers [2,5,28,36,39] may be attributed in part to entanglements and to chain stiffness due to the bulky phenyl groups positioned along the backbone of these chains. These restrictions on chain rotation and/or translation are more pronounced at temperatures below T_g . This is because the chains are associated with a minimum amount of free volume below T_g which severely hinders their segmental mobility.

The second assumption is now put forward based on the above discussion. It is believed that due to entanglements, the interlamellar amorphous regions in PEEK deforms elastically but that further deformation in this region is prohibited by entanglements and restrictions on the mobility of the chains. Because of these restrictions on the deformation of the interlamellar layer, it is felt that the crystalline lamellae must deform under the influence of further stress. Crystals are then pulled out and aligned in the direction of the applied shear, plastically deforming the crystalline regions while negligible flow occurs in the amorphous domains.

This second assumption implies that the rigid amorphous domains are already under significant strain due to crystallinity which leaves the crystalline domains alone to plastically deform in order to relieve the stress concentrations at the particle-particle interfaces. Since the elastic and viscoelastic deformations are quickly recovered within 24 hours after compaction, it is inferred from this assumption that the amorphous domains do not play a significant role in compact densification. This phenomenon is dramatically depicted in Fig. 14 by the shaded amorphous domains within the particles. Therefore, the amorphous contributions should be excluded from the DP expression (equation (1)) which determines the compaction efficiency. This modification is explained below. Also note that the particle surface indentations and the interparticle voids shown in Figs. 9 and 10 substantiate that more plastic deformation occurs in the powders of each grade which contain a higher degree of crystallinity. These observations give credence to this second assumption.

The third assumption is that due to the limited overall strain during the compaction process, the crystalline domains may be plastically deformed near the particle surfaces only without significantly reducing the degree of crystallinity of the bulk powder. This assumption was checked experimentally by performing DSC tests on shavings from the 150PF and 150P compacts, and negligible reductions in crystallinity were measured compared to the as-received powders.

The above discussion has led to the formulation of a crystalline domain based densification parameter to explain the compaction behavior of PEEK powders at room temperature. This new expression is constructed in the following paragraphs.

In order to mathematically exclude the amorphous domains from the measurement of compaction efficiency, a modified densification parameter (DP^*) is defined by:

$$DP^* = (Dg^* - Da^*) / (Dt^* - Da^*) \quad (2)$$

where, Dg^* - modified green density

$$= (M - M_{am}) / (Vg - V_{am}) = Mx / (Vx + Vv') \quad (3)$$

Da^* - modified apparent density

$$= (M - M_{am}) / (Vt - V_{am}) = Mx / (Vx + Vv) \quad (4)$$

Dt^* - modified theoretical powder density

$$= (M - M_{am}) / (Vt - V_{am}) = Mx / Vx \quad (5)$$

M_{am} - mass of amorphous domains

Mx - mass of crystalline domains

V_{am} - volume of amorphous domains

Vx - volume of crystalline domains

and where M , Vg , Va , Vv , Vv' and Vt are the same as previously defined.

Note that Dt^* is the same as the 100% crystalline density and that:

$$M = M_x + M_{am} \quad (6)$$

$$V_g = M/D_g \quad (7)$$

$$V_a = M/D_a \quad (8)$$

$$V_t = M/D_t \quad (9)$$

$$M_{am} = (1 - X)(M) \quad (10)$$

$$V_{am} = M_{am}/D_{am} \quad (11)$$

where, X = weight fraction crystallinity (Table 1)
 D_{am} = amorphous density = 1.263 g/cc [9]

A normalized compressibility curve using the modified densification parameter for the 150PF and 150P PEEK compacts is shown in Fig. 15. This figure shows that the 150P powder has a higher compaction efficiency than the 150PF powder at high pressures and a lower one at low pressures. In the plateau region this is a reversal in the relative densification order compared to Figs. 7 and 12. Based on the DP^* model described above, the higher degree of compaction efficiency in the 150P powder at high pressures is primarily attributable to its higher degree of crystallinity (Table 1). At low pressures, particle shape and particle size distribution are the predominant parameters which influence compressibility.

The green strength results normalized in terms of the modified densification parameter are graphed in Fig. 16. This figure shows that the slightly higher strength values of the 150P compacts are consistent with its higher DP^* and higher degree of crystallinity compared to the 150PF compacts. This subtle reversal in the densification order gives strong support to the role of crystallinity and plastic deformation during the compaction of PEEK.

DISCUSSION

From communication with the manufacturer [46] it was learned that the fine-sized powders of each grade are produced by mechanically grinding the respective coarse-sized powders. The powder density results show that the fine-sized powders have substantially lower densities and hence lower crystallinity values than the coarse-sized powders. The DSC results also show this same trend in the degree of crystallinity but the differences are not as pronounced as they are from the density results. However, these techniques do show that there is a reduction in crystallinity due to the mechanical grinding process. Furthermore, it is clearly evident from both DSC and density results that the 450PF powder is not fully crystallized in its as-received form. Consequently, the DSC results




Figure 15 - Modified Densification Parameter versus Compaction Pressure for 150 Grade PEEK Samples




Figure 16 - Transverse Rupture Strength versus Modified Densification Parameter for 150 Grade PEEK Samples

reveal that it is the only material which has a higher degree of crystallinity after melting and recrystallizing than it does in its as-received condition.

The compaction results indicate that there are dramatic differences between the 150 grade and 450 grade of PEEK powders. According to the manufacturer [47], the 150 grade has a melt viscosity of about 1200 P at a temperature and shear rate of 380°C and 1000/s, respectively while the 450 grade has a viscosity of about 3000 P under the same conditions. This is due to its higher molecular weight compared to the 150 grade [48]. The 450 grade also has a slightly higher yield strain than the 150 grade [47]. The 450 grade powders when compacted at pressures up to 614 MPa were not plastically deformed enough to hold the specimens together when ejected from the die. However, the 150 grade compacted quite nicely under the same conditions. Given the limited deformation during compaction, the 450 grade powders probably were not deformed sufficiently beyond their yield strain. When removed from the die, the 450 powders recovered this elastic deformation leaving the compacts with insufficient strength for handling. Since the 450 grade could not be compacted at room temperature, compaction at higher temperatures was attempted. It was reasoned that quality compacts could be obtained by compressing these powders at a temperature above their T_g . Therefore, 450 grade powders were heated to 210°C and successfully compacted in a cold die. Another technique for enhancing the plastic deformation was also implemented with the 450 grade powders by mixing them with a hard filler (nickel powder). This technique was also effective in providing good particle interlocking necessary to achieve a quality compact at room temperature [38].

The compressibility curves for the 150 grade PEEK powders are similar to those of UHMWPE [28] and other polymers [32] in that a maximum or plateau density level is reached which is below the theoretical compact density. The compacts formed under high pressures (>300 MPa) are at or very close to the theoretical density in the die. However, the elastic component of the strain is recovered when the load is removed. This recovery results in a green density which is below the theoretical powder density. The relative plateau density level of the 150 grade PEEK compacts however, ranked relatively high compared to UHMWPE [28] and other thermoplastics [32]. These high densification levels with PEEK indicate that most of the particle deformation during consolidation is attributable to plastic deformation.

Introducing the role of crystallinity into the densification parameter (DP) appears to be logical in the present PEEK systems particularly because the amorphous region is below T_g during compaction. Calculation of the DP on the basis of the crystalline content yielded the modified densification parameter (DP^*). This DP^* is based on the assumption that the plastic deformation during compaction occurs in the crystalline domains alone. Using this DP^* , the relationship between the relative plateau densities and the green strength values appears to be consistent and in agreement with other systems in the literature.

If plastic deformation is accepted as the reason for the quality of these PEEK compacts then it is easy to see that increasing the degree of

plastic deformation and mechanical interlocking can dramatically increase the green strength.

CONCLUSIONS

- 1) Semicrystalline PEEK powders were compacted at temperatures below their glass transition temperature to produce high density preforms which have enough strength for processing provided the particles can undergo sufficient plastic deformation.
- 2) Commercial 150 grade PEEK powders were compacted at room temperature to yield high quality specimens with adequate strength for handling and further processing, while the 450 grade did not undergo sufficient plastic deformation to be consolidated under the same conditions.
- 3) The fine powders (PF designated) of each grade of PEEK had markedly lower crystallinity values than their respective coarse powders. Additionally, the as-received 450PF powder underwent further crystallization when heated above the glass transition temperature.
- 4) Both 150 grade PEEK compacts reached about the same plateau or maximum density level despite differences in particle characteristics. These relative plateau density levels were 95.8% and 95.1% of the 150PF and 150P powder densities, respectively.
- 5) PEEK compact densities in the plateau region of the compressibility curve had only a slight dependence on post-compaction time since the axial dimension was expanding while the radius was contracting at nearly the same rate.
- 6) Most of the viscoelastic recovery took place within 24 hours and the total viscoelastic recovery in the radial direction was less than one half of one percent. Based on the 24 hour thickness, the axial viscoelastic recovery was also less than one half of one percent.
- 7) PEEK deformation during compaction is mainly due to plastic deformation of the crystalline regions of the polymer. The amorphous regions when below T_g are too restricted in mobility to be an important contributor to the consolidation process.
- 8) A new densification parameter, DP^* , based on the crystalline component of the polymer alone, was derived and appears to describe the compressibility and strength data consistently.

RECOMMENDATIONS FOR FUTURE WORK

The present investigation systematically exploited some of the fundamentals involved with fabricating PEEK compacts using P/M technology. Since no previous work has been reported on the cold compaction of PEEK powders, there is much need to extend this research. Additional areas which may significantly advance the state-of-the-art using this high performance polymer are suggested below.

- 1) Investigate the sintering behavior of PEEK compacts and characterize the resultant properties and the dimensional stability of the sintered product.
- 2) Exploit the use of ultrasonic compaction to fuse the polymer particles together. This may eliminate the need for a sintering step.
- 3) Utilize a dynamic (high rate) compaction technique to achieve higher green densities and to enhance plastic deformation.
- 4) Study the effect of adding conductive metal powders to the PEEK compacts to demonstrate the feasibility of fabricating conductive composites using P/M technology.

ACKNOWLEDGEMENTS

J.J.R. wishes to thank the Naval Air Systems Command (NAVAIR) Aircraft Materials Research Program and the Office of Naval Technology (ONT) Airborne Materials Block of the Navy Exploratory Development Program for their financial support. I.K. wishes to thank the Navy-ASEE Summer Faculty Program for his 1986 and 1987 summer support. The authors also wish to thank E. Lion, W. Weist, W. Green, D. Gauntt, D. Granata, L. Christiansen, J. Danovitch, W. Lin, E. Tees, S. McCallum and V. Krishnamurthy for their contributions throughout the course of this work.

LIST OF REFERENCES

1. Polymer Handbook, 2nd Ed., New York, John Wiley & Sons, Inc., edited by J. Brandrup and E. H. Immergut, V-34 (1975).
2. D. I. McCane, "Tetrafluoroethylene Polymers", Ency. of Polym. Sci. and Tech., New York, John Wiley & Sons, Inc., 13, 623 (1970).
3. G. W. Halldin and B. Bahrololoumi, "The Powder Processing of Thermoplastic Polyimide", SPE ANTEC Tech. Paper, 29, 234 (1983).
4. K. W. Rausch, Jr. and W. J. Farrissey, "Room Temperature Forming of Polyimide 2080", SPE ANTEC Tech. Paper, 22, 644 (1976).
5. D. G. Brady, "The Crystallinity of Poly(phenylene Sulfide) and Its Effect on Polymer Properties", J. Appl. Polym. Sci., 20, 2541 (1976).
6. C. C. M. Ma, J. E. O'Connor and A. Y. Lou, "Polyphenylene Sulfide High Performance Composites", SAMPE Quarterly, 15, 12, (1984).
7. P. C. Dawson and D. J. Blundell, "X-ray data for poly(aryl ether ketones)", Polymer, 21, 577 (1980).
8. T. E. Attwood, P. C. Dawson, J. L. Freeman, L. R. J. Hoy, J. B. Rose and P. A. Staniland, "Synthesis and properties of polyaryletherketones", Polymer, 22, 1096 (1981).
9. D. J. Blundell and B. N. Osborn, "The morphology of poly(aryl-ether-ether-ketone)", Polymer, 24, 953 (1983).
10. O. B. Searle and R. H. Pfeiffer, "Viktrex Poly(ethersulfone) (PES) and Viktrex Poly(etheretherketone) (PEEK)", Polym. Eng. Sci., 25, 474 (1985).
11. Technical Literature VK2, "Viktrex PEEK: A Guide To Grades For Injection Moulding", Imperial Chemical Industries, Welwyn Garden City, Hertfordshire, England (1986).
12. Technical Literature VK3, "Viktrex PEEK: A Guide To Grades For Injection Moulding", Imperial Chemical Industries, Welwyn Garden City, Hertfordshire, England (1986).
13. A. Benatar and T. G. Gutowski, "A Review of Methods for Fusion Bonding Thermoplastic Composites", SAMPE Journal, 23, 33 (1987).

14. V. Krishnamurthy and I. L. Kamel, "Powder Processing of Iron Filled Ultra High Molecular Weight Polyethylene", SPE ANTEC Tech. Paper, 33, 514 (1987).
15. V. Krishnamurthy, Powder Processing of Iron Filled Ultra High Molecular Weight Polyethylene, M.S. Thesis, Drexel University (1986).
16. J. Lew and R. T. Woodhams, "Lamination of Ordered Polyolefin Sheets by Electromagnetic Welding", SPE ANTEC Tech. Paper, 33, text on 575-576, figures on 581-584 (1987).
17. R. Gauvin, Q. X. Nguyen, J. P. Chalifoux and R. D. Bourbeau, "Investigation of the Radio Frequency Heating Process for UHMWPE", SPE ANTEC Tech. Paper, 33, text on 579-581, figures on 577-578 (1987).
18. T. Maeda and S. Matsuoka, "Study on Cold-Compacting Molding of Polymeric Powders", Journal of the Faculty of Engineering, the University of Tokyo, (B), 33 (2), 191 (1975).
19. R. J. Crawford and D. Paul, "Solid phase compaction of polymers", J. Mater. Sci., 14, 2693 (1979).
20. R. J. Crawford and D. W. Paul, "Cold compaction of polymeric powders", J. Mater. Sci., 17, 2267 (1982).
21. R. J. Crawford, D. W. Paul and D. Sprevak, "Solid phase compaction of polymeric powders: effects of compaction conditions on pressure and density variations", Polymer, 23, 123 (1982).
22. R. J. Crawford, "Effect of Compaction Rate During the Cold Forming of Polymeric Powders", Polym. Eng. Sci., 22, 300 (1982).
23. R. J. Crawford and D. Paul, "Pressures transmitted through polymeric powders subjected to solid phase compaction", Polymer, 21, 138 (1980).
24. H. K. Palmer and R. C. Rowe, "A Study of the Compaction Behaviour and Pore Structure of Polymer Compacts Using Mercury Porosimetry", Powder Technol., 10, 225 (1974).
25. K. Umeya and R. Hara, "On the Rheology of Packed Polymer Powders", Polym. Eng. Sci., 20, 778 (1980).
26. G. S. Jayaraman, J. F. Wallace, P. H. Geil and E. Baer, "Cold Compaction Molding and Sintering of Polystyrene", Polym. Eng. Sci., 16, 529 (1976).
27. K. Umeya and R. Hara, "Rheological Studies of Compaction for Polystyrene Powder", Polym. Eng. Sci., 18, 366 (1978).

28. G. W. Halldin and I. L. Kamel, "Powder Processing of Ultra-High Molecular Weight Polyethylene. I. Powder Characterization and Compaction", *Polym. Eng. Sci.*, 17, 21 (1977).
29. R. W. Truss, K. S. Han, J. F. Wallace and P. H. Geil, "Cold Compaction Molding and Sintering of Ultra High Molecular Weight Polyethylene", *Polym. Eng. Sci.*, 20, 747 (1980).
30. D. M. Bigg, "A Study of the Effect of Pressure, Time, and Temperature on High-Pressure Molding", *Polym. Eng. Sci.*, 17, 691 (1977).
31. D. M. Bigg, "High-Pressure Molding of Polymeric Powders", SPE ANTEC Tech. Paper, 21, 472 (1975).
32. G. W. Halldin and M. R. Shah, "Compaction of Polymer Powders", SPE ANTEC Tech. Paper, 27, 353 (1981).
33. T. Ross, "Review of Polymer Powder Sintering", SPE ANTEC Tech. Paper, 25, 909 (1979).
34. I. Lax, "Powder Technology of Ultra-High Molecular Weight Polyethylene Fractional Effects", SPE ANTEC Tech. Paper, 32, 1448 (1986).
35. G. W. Halldin, Powder Processing of Ultra-High Molecular Weight Polyethylene, Ph. D. Thesis, Drexel University, Department of Materials Engineering (1980).
36. S. Radhakrishnan and V. M. Nadkarni, "Modification of Surface Structure and Crystallinity in Compression-Molded Poly(Phenylene Sulfide)", *Polym. Eng. Sci.*, 24, 1383 (1984).
37. V. M. Nadkarni and S. Radhakrishnan, "Structural Investigations of Powder Processed Poly(phenylene Sulfide) Blends", *Polym. Eng. Sci.*, 27, 547 (1987).
38. J. J. Reilly and I. L. Kamel, to be published.
39. D. J. Blundell, D. R. Beckett and P. H. Willcocks, "Routine crystallinity measurements of polymers by d.s.c.", *Polymer*, 22, 707 (1981).
40. C. N. Velisaris and J. C. Seferis, "Crystallization Kinetics of Polyetheretherketone (PEEK) Matrices", *Polym. Eng. Sci.*, 26, 1574 (1986).
41. J. M. Schultz, Polymer Material Science, New Jersey, Prentice-Hall, Inc., Chapter 11 (1974).
42. D. J. Kemmish and J. N. Hay, "The effect of physical ageing on the properties of amorphous PEEK", *Polymer*, 26, 905 (1985).

43. A. Karbach, "Plastic deformation of thin films of poly(ether ether ketone)", Polym. Comm., 28, 24 (1987).
44. I. Kamel and L. Finegold, "A Model for Radiation-Induced Changes in Ultrahigh-Molecular-Weight Polyethylene", J. Polym. Sci., Polym. Phys. Ed., 23, 2407 (1985).
45. I. Kamel and L. Finegold, "Effect of Radiation on the Structure of Ultrahigh Molecular Weight Polyethylene", Radiat. Phys. Chem., 26 (6), 685 (1985).
46. R. H. Pfeiffer, Private Communication (November 1986).
47. Technical Literature VKT3, "Viktrex PEEK: Easy Flow Grades", Imperial Chemical Industries, Welwyn Garden City, Hertfordshire, England (1985).
48. W. R. Bergenn, Private Communication (November 1986).

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

IBM Almaden Research Center.....	1
650 Harry Road	
San Jose, CA 95120	
Attn: Dr. A. Zachariades	
 Texas A & M University.....	1
Department of Mechanical Engineering	
College Station, TX 77843	
Attn: Dr. G. Halldin	
 Ecole Polytechnique de Montreal.....	1
Mechanical Engineering Department	
P. O. Box 6079, Station "A"	
Montreal, Quebec	
Canada H3C 3A7	
Attn: Dr. R. Gauvin	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

BASF Structural Materials, Inc.....	1
379 Cartwright Drive	
Fairlawn, OH 44313	
Attn: M. Chin	
 BASF Structural Materials, Inc.....	 2
11501 Steele Creek Road	
P. O. Box 7687	
Charlotte, NC 28217	
Attn: G. E. Husman	
S. R. Clemans	
 Western New England College.....	 1
Department of Electrical Engineering	
Springfield, MA 01119	
Attn: Dr. J. V. Masi	
 AI Technology, Inc.....	 1
P. O. Box 3081	
Princeton, NJ 08543	
Attn: Dr. K. K. T. Chung	
 ICI Americas Inc.....	 3
Wilmington, DE 19897	
Attn: R. H. Pfeiffer	
W. R. Bergenn	
C. H. Price	
 Sherritt Gordon Mines Limited.....	 2
Fort Saskatchewan, Alberta	
Canada T8L 2P2	
Attn: K. Hajmrle	
C. Tunney	
 Honeywell Inc.....	 1
Systems and Research Center	
3660 Technology Drive	
P. O. Box 1361 (MN65-2600)	
Minneapolis, MN 55418	
Attn: A. J. Rholl	
 Advanced Technology Materials, Inc.....	 2
520-B Danbury Road	
New Milford, CT 06776	
Attn: Dr. W. C. Stevens	
Dr. B. Luxon	
 Damaskos, Inc.....	 2
P. O. Box 469	
Concordville, PA 19331	
Attn: N. Damaskos	
Dr. W. J. Biter	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

DuPont Company.....	1
Engineering Technology Laboratory	
Experimental Station Bldg. 304/A107	
Wilmington, DE 19898	
Attn: Dr. P. S. Kezios	
 Chevron Chemical Company.....	 1
Olefins and Derivatives Division	
Orange, TX 77630	
Attn: G. L. Baker	
 Coating Sciences, Inc.....	 1
48 E. Newberry Road	
Bloomfield, CT 06002	
Attn: R. Kumar	
 LNP Corporation.....	 1
412 King Street	
Malvern, PA 19355	
Attn: D. G. Lane	
 E/M Corporation.....	 1
P. O. Box 2200	
West Lafayette, IN 47906	
Attn: Dr. R. M. Gresham	
 E/M Corporation.....	 1
900 Calcon Hook Road	
Sharon Hill, PA 19079	
Attn: J. W. Taylor	
 Thermofil Inc.....	 1
6150 Whitmore Lake Road	
P. O. Box 489	
Brighton, MI 48116	
Attn: M. Balow	
 Micromeritics.....	 1
One Micromeritics Drive	
Norcross, GA 30093-1877	
Attn: S. J. Kirk	
 BASF Structural Materials, Inc.....	 1
95 Madison Avenue, M/S CN 1989	
Morristown, NJ 07960	
Attn: Dr. R. Davitt	
 BASF Structural Materials, Inc.....	 1
1440 N. Kraemer Boulevard	
Anaheim, CA 92806	
Attn: R. H. Fuse	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

Naval Air Engineering Center.....	1
Lakehurst, NJ 08733	
Attn: D. Snedaker, Code 9452	
Locus, Inc.....	1
2560 Huntington Ave.	
Alexandria, VA 22303	
Attn: R. Steele	
IIT Research Institute (DDN).....	1
185 Admiral Cochrane Drive	
Annapolis, MD 21401	
Attn: S. Timerman	
Naval Safety Center.....	1
Norfolk, VA 23511	
Attn: CW02 R. Valdillez, Code 121	
Raychem Corporation.....	1
300 Constitution Drive	
Menlo Park, CA 94025	
Attn: R. Dubrow	
FMC-NSD.....	1
4800 East River Road, MS T420	
Minneapolis, MN 55421	
Attn: R. Horst	
Drexel University.....	6
Department of Materials Engineering	
32nd & Chestnut Streets	
Philadelphia, PA 19104	
Attn: Dr. I. L. Kamel (5)	
Dr. R. D. Corneliussen (1)	
Paragon Development Corporation.....	1
18-B Kripes Road	
East Granby, CT 06026	
Attn: W. W. Hart	
Celanese Specialty Operations.....	1
86 Morris Avenue	
Summit, NJ 07901	
Attn: J. B. Flynn	
Coats & Clark Inc.....	1
Specialty Products Division - Research	
P. O. Box 670	
Rose Lane	
Toccoa, GA 30577	
Attn: J. M. Rees	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

J. F. Taylor, Inc.....	1
South Three Notch Rd.	
P. O. Box 760	
Lexington Park, MD 20653	
Attn: R. C. Fowler	
Chief of Naval Operations.....	1
Washington, DC 20350	
Attn: R. Haislmaier, Code OP941F	
National Bureau of Standards.....	1
Gaithersburg, MD 20899	
Attn: J. Horlick, ADMIN-A531	
National Bureau of Standards.....	1
325 Broadway	
Boulder, CO 80303	
Attn: G. Reeve, Code 723.00	
Evaluation Research Corp.....	1
5510 Morehouse Dr.	
San Diego, CA 92120	
Attn: W. Johnson	
ERC International.....	1
1725 Jefferson Davis Hwy.	
Suite 300	
Fairfax, VA 22202	
Attn: G. Johnston	
Jet Propulsion Laboratory.....	1
4800 Oak Grove Dr.	
Pasadena, CA 91109	
Attn: R. Kuberry	
Atlantic Research Corporation.....	1
16 Danube Drive	
King George, VA 22485	
Attn: W. B. McDougal	
Space and Naval Warfare Command.....	2
Washington, D. C. 20350	
Attn: Capt. R. Plante	
J. Tedder, Code 32D1	
Special Projects/Services.....	1
7875 Convoy Court, Suite Five	
P. O. Box 178308	
San Diego, CA 92117	
Attn: A. J. Rowe	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

SFS Industries.....	3
13767 Freeway Drive	
Santa Fe Springs, CA 90670	
Attn: M. Haduk	
T. Sobol	
T. Sobol	
 Haskon Corporation.....	 1
336 Weir Street	
Taunton, MA 02780	
Attn: E. Freeman	
 Parker Seal.....	 1
2360 Palumbo Drive	
Lexington, KY 40512	
Attn: H. Choudhary	
 Clemson University, ECE Department.....	 1
Clemson, SC 29634-0915	
Attn: J. Bennett	
 NAVAIRDEVCE.....	 46
(3 for Code 8131)	
(40 for Code 6064)	
(3 for Code 7053)	
 Pacific Missile Test Center.....	 3
Point Mugu, CA 93042	
Attn: J. Boone, Code 4034	
K. Knudsen, Code 4034	
R. Rodgers, Code 2043	
 Naval Ocean Systems Center.....	 2
San Diego, CA 92152	
Attn: L. Bossert, Code 825	
W. Cronyn, Code 825	
 Lectromechanical Design Co.....	 1
13510 Glendundee Dr.	
Herndon, VA 22071-3322	
Attn: A. M. Bruning	
 ORI, Inc.....	 1
444 Jacksonville Road	
Warminster, PA 18974-5000	
Attn: M. Daniele	
M. Massaro	
 Naval Aviation Depot.....	 3
Alameda, CA 94501	
Attn: N. H. Duong, Code 35220	
D. Romano, Code 313	
Code 340	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

Naval Air Force, U.S. Pacific Fleet.....	2
NAS North Island	
San Diego, CA 92135-5100	
Attn: B. Fusco, AIRPAC 7412	
AECS W. Shipley, Code 7210C	
Naval Aviation Engineering Service Unit.....	50
Philadelphia, PA 19112	
Attn: Code 018	
Distribution to all NAESU Corrosion Representatives	
Naval Aviation Depot.....	3
NAS, Norfolk, VA 23511	
Attn: Code 340	
J. Cole, Code 311	
R. Watkins, Code 32120	
Naval Aviation Depot.....	2
NAS, Jacksonville, FL 32212	
Attn: Code 340	
B. Beaman, Code 352	
Naval Aviation Depot.....	2
NAS, Pensacola, FL 32508	
Attn: Code 340	
M. W. Johnson, Code 321	
G. Locklar, Code 321	
Naval Sea Systems Command Headquarters.....	4
Washington, DC 20362	
Attn: SEA-05E1	
SEA-05M1	
D. Cross, SEA-06Q122	
R. Hynes, SEA-06DE5	
Naval Sea Systems Command.....	1
Washington, DC 20361	
Attn: J. White, SEA-6522	
Shielding Systems.....	1
1245 Good Hope Farm Road	
Aiken, SC 29801	
Attn: J. Hicks	
Elastomer Composite Technologies.....	1
2401 S. Pullman Street	
Santa Anna, CA 92799-5056	
Attn: H. Sexson	
TA Manufacturing Company.....	2
375 W. Arden Avenue	
Glendale, CA 91203	
Attn: K. Brown	
B. Fisher	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

DOW Chemical U.S.A.....	2
Electronic Business Development	
2020 Willard H. Dow Center	
Midland, MI 48674	
Attn: E. Lane	
M. Murry	
DOW Chemical U.S.A.....	1
Electronic Business Unit	
Bldg. 2502	
Plaquemine, LA 70765-0400	
Attn: Dr. T. Bohnert	
Naval Ship Engineering Center.....	1
Navy Department	
Washington, DC 20360	
Attn: Code 6101E	
NASA Headquarters.....	1
600 Independence Avenue, S.W.	
Washington, DC 20546	
Attn: N. Mayer, Code RV-2	
Office of Naval Research.....	1
Washington, DC 20350	
Attn: Code 472	
Office of Naval Research, Boston.....	1
495 Summer Street	
Boston, MA 02210	
Naval Surface Weapons Center.....	2
White Oak, Silver Spring, MD 20910	
Attn: Code 234	
G. Bechtold, Code H25	
Naval Air Propulsion Center.....	2
Trenton, NJ 08628-0176	
Attn: J. Glatz	
R. Vizzini, Code PE32	
Commander.....	1
Naval Weapons Center	
China Lake, CA 93555	
Attn: R. Christiansen, Code 36254	
Naval Air Force, U.S. Atlantic Fleet.....	3
NAS Norfolk	
Norfolk, VA 23511-5188	
Attn: G. Browne, AIRLANT 528	
AIRLANT 522	
AEC F. Zumbro	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

Lockheed California Company.....	1
Box 551	
Burbank, CA 91520	
Attn: J. Wooley	
Lockheed-Georgia Company.....	1
Marietta, GA 30063	
Attn: L. Meade	
Lockheed Missiles & Space Company.....	1
Sunnyvale, CA 94088	
Attn: H. Armstrong, Dept. 62-60	
David W. Taylor R & D Center.....	1
Bethesda, MD 20084	
Attn: M. Krenzke, Code 1730	
NASA.....	1
Langley Research Center	
Hampton, VA	
Attn: B. Stein	
United Aircraft Corporation.....	1
Sikorsky Aircraft Division	
Stratford, CT 06602	
Attn: J. Ray	
Naval Aviation Depot.....	5
Mail Stop No. 9	
MCAS Cherry Point, NC 28533-5030	
Attn: T. Fuss, Code 343	
J. Strohenberg	
W. Bach, Code 840A	
R. Day, Code 35120	
Code 340	
Army Materials & Mechanics Research Center.....	2
Polymers & Chemistry Division	
Watertown, MA 02172	
Attn: G. Hagnauer	
R. Sacher	
Defense Technical Information Center.....	12
Cameron Station, Bldg. 5	
Alexandria, VA 23314	
Attn: DTIC-DDA-1	
DOW Chemical U.S.A.....	2
Polymeric Materials Laboratory	
1712 Bldg.	
Midland, MI 48674	
Attn: J. Gamble	
Dr. T. Regulski	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

General Dynamics.....	1
Convair Division	
P. O. Box 1128	
San Diego, CA 92138	
Attn: W. Scheck, Dept. 572-10	
 General Dynamics.....	 2
Fort Worth Division	
Mail Zone 2161	
P. O. Box 748	
Fort Worth, TX 76101	
Attn: J. Peoples	
J. Burns	
 Litton Systems Inc.....	 2
Amecom Division	
5115 Calvert Road	
College Park, MD 20740-3898	
Attn: J. Merritt	
C. Auletta	
 Naval Underwater Systems Center.....	 1
Electromagnetic Systems Integration Division	
New London, CT 06320	
Attn: D. Dixon, Code 3431	
 Phillips Petroleum Company.....	 1
Research and Development	
Room 115, Bldg. 71-C, PRC	
Bartlesville, OK 74004	
Attn: B. Benazza	
 Air Force Materials Laboratory.....	 6
Wright-Patterson Air Force Base	
Dayton, OH 45433	
Attn: M. Forte, AFALD/PTEM (1)	
Codes LC (1)	
LN (1)	
LTF (1)	
LAE (1)	
MBC (1)	
 Air Force Dynamics Laboratory.....	 1
Wright-Patterson Air Force Base	
Dayton, OH 45433	
Attn: Code FDTC	
 U. S. Army Air Mobility R & D Laboratory.....	 1
Fort Eustis, VA 23604	
Attn: SAVDL-EU-SS	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

Allied Amphenol Products.....	2
Bendix Connector Operations	
40-60 Delaware Street	
Sidney, NY 13838-1395	
Attn: J. Becker	
R. Piscitelli	
The Pyle-National Company.....	1
1334 North Kostner Avenue	
Chicago, IL 60651	
Attn: D. Carlson	
Deutsch, Electronic Components Division.....	2
Municipal Airport	
Banning, CA 92220	
Attn: T. Linder	
E. Meelhuysen	
G & H Technology, Inc.....	2
750 W. Ventura Blvd.	
Camarillo, CA 93010	
Attn: G. Walters	
Dr. C. Dutcher	
AMP Inc.....	2
Industrial Division	
Harrisburg, PA 17105-3608	
Attn: F. Fischer	
R. Juchem Jr.	
AMP Inc.....	2
R. D. #2	
Glen Rock, PA 17327	
Attn: F. Koblitz	
D. Sorenson	
AMP Inc.....	1
Industrial Division	
North Atlantic Aerospace District	
9 Lafferty Drive	
Cherry Hill, NJ 08002	
Attn: R. Lubenow	
Tempo Instrument Inc.....	2
87 Modular Avenue	
Commack, NY 11725	
Attn: C. Simonsen	
M. Ellars	
Rome Air Development Center.....	1
Product Evaluation Branch	
Griffiss AFB, NY 13441-5700	
Attn: L. Lorang, LT.	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

Naval Aviation Depot.....	5
NAS North Island	
San Diego, CA 92135	
Attn: M. Albers, F/A-18 Air Vehicle Engineering	
H. D. Caldwell, Code 731	
T. L. Rigsby, Code 7271E	
M. J. Schmidt, Code 31213	
Code 340	
Naval Avionics Center.....	7
6000 East 21st Street	
Indianapolis, IN 46219-2189	
Attn: D. Lee, Code 916	
W. Swift, Code B/443	
K. Hines, Code B/443	
H. Stone, Code 440	
R. Morgan, Code 832	
N. Lee, Code 814	
T. Adler, Code 814	
Dow Corning Corporation.....	1
Specialty Aerospace Materials	
Technical Service & Development	
Midland, MI 48686	
Attn: W. Nicholson	
Westinghouse Electric Corporation.....	3
Defense and Electronics Center	
P. O. Box 746	
Baltimore, MD 21203	
Attn: M. S. Schroeder, MS 496	
K. D. Romer, MS 1112	
J. D. Gardner, Jr., MS 496	
Naval Air Test Center.....	4
Patuxent River, MD 20670	
Attn: F. Heather, SY-82	
R. Rakoski, SY-60	
K. Brezinski, SY-60	
V. Demko, SY-60	
Northwest Technical Industries, Inc.....	1
1840 18th Street N. W.	
Washington, DC 20009	
Attn: P. Stranges	
Northwest Technical Industries, Inc.....	1
547 Diamond Point Road	
Sequim, WA 98382	
Attn: A. Hare	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

ECS Composites.....	2
3560 Rogue River Highway	
P. O. Box 188	
Grants Pass, OR 97526	
Attn: D. Becklin	
J. Narmore	
Novamet.....	1
10 Lawlins Park	
Wyckoff, NJ 07481	
Attn: L. Koehler	
Potters Industries Inc.....	3
377 Route 17	
P. O. Box 86	
Hasbrouck Heights, NJ 07604	
Attn: G. Balcar	
L. Chazen	
Dr. J. Walther	
National Standard.....	1
236 Timber Creek Lane	
Marietta, GA 30060	
Attn: J. Toon	
Inland Manufacturing.....	4
2775 E. La Cadena Drive	
Riverside, CA 92507	
Attn: M. Michaelis	
B. Stewart	
C. Albo	
Dr. D. Dixon	
Northrop Corporation.....	2
One Northrop Avenue	
Hawthorne, CA 90250	
Attn: V. Shrader, Dept. 3881/94	
R. Leffall, Dept. 3881/94	
Products Research & Chemical Corporation.....	2
5430 San Fernando Road	
Glendale, CA 91203	
Attn: R. Lau	
T. Clark	
Products Research & Chemical Corporation.....	2
Research Laboratories	
2820 Empire Avenue	
Burbank, CA 91504	
Attn: S. Randazzo	
A. Sharaby	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-38026-60

Naval Surface Weapons Center.....	3
Dahlgren, VA 22448	
Attn: S. Campbell	
J. Bryant, Code H24	
M. Guthrie, Code H11	
W. Lenzi, Code H22	
Naval Electronics Systems Engineer Center.....	1
P. O. Box 55	
Portsmouth, VA 23705-0055	
Attn: L. Larrow	
Intercal Company.....	1
1600 Washington Avenue	
Port Huron, MI 48060	
Attn: G. Davis	
Isolation Technology, Inc.....	1
321 E. Haley Street	
P. O. Box 22808	
Santa Barbara, CA 93121	
Attn: J. Flavin	
Isolation Technology, Inc.....	1
321 E. Haley Street	
P. O. Box 21208	
Santa Barbara, CA 93121	
Attn: L. Reading	
Spira Manufacturing Corporation.....	1
12721 Saticoy Street, So.	
Unit B	
N. Hollywood, CA 91605	
Attn: G. Kunkel	
SRS Industries.....	1
9433 Hyssop Dr.	
Rn Cucamonga, CA 91730-6017	
Trakka Corporation.....	1
14 Bisset Drive	
W. Milford, NJ 07480	
Attn: H. Charles	
Techna-Plastics.....	1
P. O. Box 298	
Lehighnton, PA 18235	
Attn: J. Barilla	
RTP Company.....	1
29120 Vista Valley Drive	
Vista, CA 92084	
Attn: H. Christensen	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

American Cyanamid Company.....	1
Polymer Products Division	
South Cherry St.	
Wallingford, CT 06492	
American Cyanamid Company.....	1
One Cyanamid Plaza	
Wayne, NJ 07470	
Attn: J. Tonges	
NASA.....	1
Goddard Space Flight Center	
Greenbelt, MD 20771	
Attn: Dr. S. Lee, Code 313.2	
PCK Elastomerics, Inc.....	1
2940 Turnpike Drive	
Hatboro, PA 19040	
Attn: Dr. L. Buchoff	
Technit.....	4
129 Dermody Street	
Cranford, NJ 07016	
Attn: P. Grant	
G. Lyman	
C. Dalamangas	
D. Molnar	
Naval Air Systems Command.....	12
Washington, DC 20361	
Attn: D. Moore, AIR-5304 (3)	
D. Jamieson, AIR-41113E (1)	
S. Chernin, AIR-4111C (1)	
L. Slotter, AIR-931A (1)	
R. Carstensen, AIR-5161 (2)	
E. Demaret, AIR-5002 (1)	
A. Iacono, AIR-5161B (1)	
R. Hammett, AIR-5161C (1)	
D. Fellin, AIR-5161G (1)	
Naval Research Laboratory.....	8
Washington, DC 20375-5000	
Attn: Dr. Rm. Panayappan, Code 6173	
Dr. J. Cooper, Code 6173	
F. J. Campbell, Code 4654	
R. Ford, Code 5330	
M. C. Li, Code 5733A	
P. Schoen, Code 6190	
Code 6306	
Code 6120	

DISTRIBUTION LIST (CONTINUED)

REPORT NO. NADC-88026-60

Hughes Aircraft.....	1
Bldg. E1, MS F180	
El Segundo, CA 90245	
Attn: A. Winslow	
Martin Marietta.....	1
103 Chesapeake Park Plaza	
Baltimore, MD 21220	
Attn: J. Bird	
Martin Marietta Aerospace.....	1
P. O. Box 5837 MP1330	
Orlando, FL 32855	
Attn: J. J. Hammer	
Martin Marietta Energy Systems, Inc.....	2
P. O. Box X	
Oak Ridge, TN 37831	
Attn: P. D. Ewing	
R. A. Hess	
Oak Ridge National Laboratory.....	1
P. O. Box X	
Oak Ridge, TN 37831	
Attn: R. Hess	
Boeing Aerospace Company.....	1
P. O. Box 3999, MS 2E-01	
Seattle, WA 98124-2499	
Attn: S. Eisner	
Boeing Aerospace Company.....	2
P. O. Box 3999, MS 88-23	
Seattle, WA 98124-2499	
Attn: E. Groshart	
P. Tjelle	
Boeing-Vertol Company.....	1
P. O. Box 16858	
Philadelphia, PA 19152	
Attn: Dept. 1951	
AFWAL/MLSA.....	1
Wright Patterson AFB	
Dayton, Ohio 45433-6503	
Attn: G. Slenski	
Grace Chomerics, Inc.....	1
77 Dragon Court	
Woburn MA 01888	
Attn: E. Carlson	

DISTRIBUTION LIST

REPORT NO. NADC-88026-60

No. of Copies

Motorola, Inc.....	1
Government Electronics Division	
8201 E. McDowell Road	
P.O. Box 1417	
Scottsdale, AZ 84252	
Attn: D. Averkamp	
Conductive Systems, Inc.....	1
R. D. #1, Rt. 5 South	
Box 1040	
Amsterdam, NY 12010	
Attn: J. Severinsen	
Electro-Kinetic Systems, Inc.....	1
701 Chestnut Street	
Trainer, PA 19013	
Attn: J. T. Hoback	
Craig Systems.....	1
10 Industrial Way	
Amesbury, MA 01913	
Attn: G. Brox	
SYS.....	1
Two Governor Park	
6310 Greenwich Drive	
San Diego, CA 92122	
Attn: G. DeLong	
Miller Trailer Inc.....	1
P. O. Box 511	
Bradenton, FL 33505	
Attn: D. Kastner	
McDonnell Douglas Aircraft.....	6
P. O. Box 516	
St. Louis, MO 63166	
Attn: W. Wright	
A. Y. Pierce	
G. L. Dolan	
E. Yarbrough	
C. Fulton	
S. Clinch	
Hughes Aircraft.....	1
2000 El Segundo Blvd.	
Bldg. F-150	
El Segundo, CA 90245	
Attn: T. Wang, Code E1	

END

DATE

FILMED

11-88

DTIC